



Brazing alloy BrazeTec 21/80

Composition (% in weight)

Ag	Cu	Zn	Sn	Si	Р	Mn	Ni	Other	ISO 17672	EN 1044:1999	ISO 3677
-	Rest	-	-	-	-	12	2	-	Cu 595	-	-

Technical data:

Melting range (°C)	965-1000		
Working temperature (°C)	990		
Melting range according to DSC measurement (°C)	-		
Min. brazing temperature (°C)	-		
Electrical conductibility (m/ Ω mm ²)	-		
Elongation %	-		
Density (g/cm³)	8,8		
Shear strength (MPa)	200-300		
Tensile strength DIN EN 12797 (MPa)	-		
Operating temperature of brazed joint (min/max) \pm (°C)	-		

Applications

Tool industry

Operating conditions

Copper based alloy with excellent flow, capillarity and mechanical strength characteristics. Suitable for brazing cemented carbides, steel, nickel and nickel alloys. It is mainly used with furnace under protective atmosphere, due to the high working temperature. Free from Zn.

Recommended fluxes

H spezial, H 285, S spezial

Heat sources

Induction heating, furnace in vacuum or under protective atmosphere

Delivery forms

Wire, ring

Notes

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations. Italbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of suitability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.