



Brazing alloy BrazeTec 49/Cuplus

Composition (% in weight)

Ag	Cu	Zn	Sn	Si	P	Mn	Ni	Other	ISO 17672	EN 1044:1999	ISO 3677
49	27,5	20,5	-	-	-	2,5	0,5	-	-	-	-

Technical data:

Melting range (°C)	670-690
Working temperature (°C)	690
Melting range according to DSC measurement (°C)	-
Min. brazing temperature (°C)	-
Electrical conductivity (m/Ω mm ²)	-
Elongation %	-
Density (g/cm ³)	9
Shear strength (MPa)	150-300
Tensile strength DIN EN 12797 (MPa)	-
Operating temperature of brazed joint (min/max) ± (°C)	200

Applications

Tool industry

Operating conditions

Silver based alloy with copper interlayer to compensate the internal stresses of the joint. Excellent flow, capillarity and mechanical strength characteristics. Mechanical strength improved of 20% compared to 49/Cu alloy. Suitable for brazing cemented carbides and steel.

Recommended fluxes

H spezial, H 285

Heat sources

Flame, induction heating

Delivery forms

Tri-foil: ribbon, preforms

Notes

-

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations. Italbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of suitability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.

Italbras S.p.A.

Strada del Balsego, 6 – 36100 Vicenza (I)
info@italbras.it - www.italbras.it -
 Tel. +39 0444.3475-00 / Fax +39 0444.3475-01