



Brazing alloy BrazeTec 503

Composition (% in weight)

F	\g	Cu	Zn	Sn	Si	Р	Mn	Ni	Other	ISO 17672	EN 1044:1999	ISO 3677
	5	55	39,85	-	0,15	-	-	-	-	Ag 205	AG 208	-

Technical data:

Melting range (°C)	820-870			
Working temperature (°C)	860			
Melting range according to DSC measurement (°C)	-			
Min. brazing temperature (°C)	-			
Electrical conductibility (m/ Ω mm ²)	-			
Elongation %	-			
Density (g/cm³)	8,3			
Shear strength (MPa)	-			
Tensile strength DIN EN 12797 (MPa)	with S 235:350; with E 295:400			
Operating temperature of brazed joint (min/max) ± (°C)	-			

Applications

Refrigeration, air conditioning and electrical industry, plumbing technology

Operating conditions

Silver based brazing alloy with excellent flow, capillarity and mechanical strength characteristics. Used for brazing any steels, copper and copper alloys, as well as nickel and nickel alloys.

Recommended fluxes

N1/T, Super 1, N2/E, H paste, RS/A, FN/E, D 98, H 280

Heat sources

Induction heating, flame, furnace in vacuum and under protective atmosphere

Delivery forms

Wire, rods, ribbon, rings, preforms, powder

Notes

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations. Italbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of suitability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.