



Brazing is BrazeTec 

Brazing Flux BrazeTec FN/E Powder

Composition and technical data:

Composition (% in weight)	Borin compound, Fluorides
Colour	White
Working temperature (°C)	750-1000
Density (g/cm ³)	-
Chemical characteristics	Hygroscopic
PH	-
Solubility	-
State of product	Powder
Residues	-
Standard ISO 18496	FH20 A
Shelf life	6 months, but only in the original sealed container

Applications

Mechanical engineering

Operating conditions

Flux for brazing process. Excellent for removing surface oxides. Used for joining steel, copper and copper alloys, as well as nickel and nickel alloys.

Recommended alloys

BrazeTec BR6, BR12, OT560, OT506, OT510, OTSI, 1204, 503

Heat source

Flame, induction heating

Notes

Suitable for brazing at high temperatures

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations. Italbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of suitability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.

Italbras S.p.A.

Strada del Balsego, 6 – 36100 Vicenza (I)
info@italbras.it - www.italbras.it -
 Tel. +39 0444.3475-00 / Fax +39 0444.3475-01