



Brazing alloy in paste BrazeTec 1130

Composition (% in weight)

Ag	Cu	Zn	Sn	Si	P	Mn	Ni	Other	ISO 17672	EN 1044:1999	ISO 3677
-	-	-	-	8	2	-	Rest	18 Cr	-	-	B-Ni72Cr18SiP-1050/1090

Technical data:

Melting range (°C)	1050-1090
Working temperature (°C)	1080
Melting range according to DSC measurement (°C)	-
Minimum brazing temperature (°C)	-
Boiling point (°C)	-
Flash point (°C)	-
Operating temperature of brazed joint (°C)	-
Tensile strength DIN EN 12797 (MPa)	-
Alloy density (g/cm ³)	7,7
Paste density (g/cm ³)	3,8 (20°C)
Metal content (%) of total weight	85
Grain size of brazing alloy powder (µm)	<106
Viscosity (dPas)	400-550 (Haake Viscotester 02, Sp.2, 20 ± 2°C)
Cleaning agent	Water
Flux type within the paste	Absent
Shelf life	6 months, but only in the original sealed container at storage temperatures between +5 to +30°C

Applications

Refrigeration and air conditioning industry, heating system, automotive

Operating conditions

Homogeneous mixture of nickel based powder. Finely dissolved in a binder system water based; dosable or spreadable manually. Good flow, capillarity and mechanical strength characteristics. Used for joints in steel, stainless steel, as well as nickel, nickel alloys, cobalt, cobalt alloys, and in certain conditions special alloys.

Heat source

Furnace in vacuum and under protective atmosphere

Standard packaging

Jar

Note

-

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations. Italbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of suitability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.

Italbras S.p.A.

Strada del Balsego, 6 – 36100 Vicenza (I)
info@italbras.it - www.italbras.it -
 Tel. +39 0444.3475-00 / Fax +39 0444.3475-01